



PCT

526 Rec'd PCT/PTO 14 JUL 2000

FORM PTO-1390 (Modified) (REV 5-93)		U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE		ATTORNEY'S DOCKET NUMBER	
TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371				051009/0125	
		U.S. APPLICATION NO. (If known, see 37 C.F.R. 1.51)		UNASSIGNED 09/600277	
INTERNATIONAL APPLICATION NO. PCT/EP99/00801		INTERNATIONAL FILING DATE 06 February 1999		PRIORITY DATE CLAIMED 13 February 1998	
TITLE OF INVENTION SAUSAGE CASING WITH STARCH OR STARCH DERIVATIVES AND METHOD FOR PRODUCING THE SAME					
APPLICANT(S) FOR DO/EO/US Klaus-Dieter HAMMER, Gerhard Grolig and Michael Ahlers					
Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:					
1.	<input checked="" type="checkbox"/>	This is a FIRST submission of items concerning a filing under 35 U.S.C. 371.			
2.	<input type="checkbox"/>	This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371.			
3.	<input checked="" type="checkbox"/>	This express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).			
4.	<input type="checkbox"/>	A proper Demand for International Preliminary Examination was made by the 19 th month from the earliest claimed priority date.			
5.	<input checked="" type="checkbox"/>	A copy of the International Application as filed (35 U.S.C. 371(c)(2)) <input type="checkbox"/> is transmitted herewith (required only if not transmitted by the International Bureau). <input checked="" type="checkbox"/> has been transmitted by the International Bureau. <input type="checkbox"/> is not required, as the application was filed in the United States Receiving Office (RO/US)			
6.	<input checked="" type="checkbox"/>	A translation of the International Application into English (35 U.S.C. 371(c)(2)).			
7.	<input checked="" type="checkbox"/>	Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3)) <input type="checkbox"/> are transmitted herewith (required only if not transmitted by the International Bureau). <input type="checkbox"/> have been transmitted by the International Bureau. <input type="checkbox"/> have not been made; however, the time limit for making such amendments has NOT expired. <input checked="" type="checkbox"/> have not been made and will not be made.			
8.	<input type="checkbox"/>	A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).			
9.	<input checked="" type="checkbox"/>	An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).			
10.	<input type="checkbox"/>	A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).			
Items 11. to 16. below concern other document(s) or information included:					
11.	<input checked="" type="checkbox"/>	An Information Disclosure Statement under 37 CFR 1.97 and 1.98.			
12.	<input checked="" type="checkbox"/>	An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.			
13.	<input checked="" type="checkbox"/>	A FIRST preliminary amendment. <input type="checkbox"/> A SECOND or SUBSEQUENT preliminary amendment.			
14.	<input type="checkbox"/>	A substitute specification.			
15.	<input type="checkbox"/>	A change of power of attorney and/or address letter.			
16.	<input type="checkbox"/>	Other items or information:			

U.S. APPLICATION NO. (If known, see 37 CFR 1.50) UNASSIGNED		INTERNATIONAL APPLICATION NO. 09/600277 PCT/EP99/00801		ATTORNEY'S DOCKET NUMBER 051009/0125	
17. <input checked="" type="checkbox"/> The following fees are submitted:				CALCULATIONS	
Basic National Fee (37 CFR 1.492(a)(1)-(5): Search Report has been prepared by the EPO or JPO \$840.00					
International preliminary examination fee paid to USPTO (37 CFR 1.482) \$670.00					
No international preliminary examination fee paid to USPTO (37 CFR 1.482) but international search fee paid to USPTO (37 CFR 1.445(a)(2)) \$690.00					
Neither international preliminary examination fee (37 CFR 1.482) nor International search fee (37 CFR 1.445(a)(2)) paid to USPTO \$970.00					
International preliminary examination fee paid to USPTO (37 CFR 1.482) and all claims satisfied provisions of PCT Article 33(2)-(4) \$96.00					
ENTER APPROPRIATE BASIC FEE AMOUNT =				\$840.00	
Surcharge of \$130.00 for furnishing the oath or declaration later than 20 Months from the earliest claimed priority date (37 CFR 1.492(e))					
Claims	Number Filed	Included in Basic Fee	Extra Claims	Rate	
Total Claims	12	- 20	= 0	x \$18.00	\$0.00
Independent Claims	1	- 3	= 0	x \$78.00	\$0.00
Multiple dependent claim(s) (if applicable)				\$260.00	
TOTAL OF ABOVE CALCULATIONS =				\$840.00	
Reduction by 1/2 for filing by small entity, if applicable. Verified Small Entity statement must also be filed. (Note 37 CFR 1.9, 1.27, 1.28).				\$0.00	
SUBTOTAL =				\$840.00	
Processing fee of \$130.00 for furnishing English translation later the 20 months from the earliest claimed priority date (37 CFR 1.492(f)).				+	
TOTAL NATIONAL FEE =				\$840.00	
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property +				\$40.00	
TOTAL FEES ENCLOSED =				\$880.00	
				Amount to be:	
				refunded \$	
				charged \$	
<p>a. <input checked="" type="checkbox"/> A check in the amount of \$880.00 to cover the above fees is enclosed.</p> <p>b. <input type="checkbox"/> Please charge my Deposit Account No. <u>19-0741</u> in the amount of \$-0- to the above fees. A duplicate copy of this sheet is enclosed.</p> <p>c. <input checked="" type="checkbox"/> The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. <u>19-0741</u>. A duplicate copy of this sheet is enclosed.</p>					
<p>NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.</p>					
<p>SEND ALL CORRESPONDENCE TO:</p> <p>Foley & Lardner Washington Harbour 3000 K Street, N.W., Suite 500 Washington, D.C. 20007-5109</p>					
<p style="text-align: right;">  SIGNATURE <u>34,649</u> </p> <p style="text-align: right;">  NAME RICHARD L. SCHWAAB </p> <p style="text-align: right;">REGISTRATION NUMBER 25,479</p>					

Atty. Dkt. No. 051009/0125

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant: Klaus-Dieter HAMMER et al.
Title: SAUSAGE CASING WITH STARCH OR STARCH DERIVATIVES AND METHOD
FOR PRODUCING THE SAME
Appl. No.: UNASSIGNED
Filing Date: July 14, 2000
Examiner: Not yet assigned
Art Unit: Not yet assigned

PRELIMINARY AMENDMENT

Assistant Commissioner for Patents
Washington, D.C. 20231

Sir:

Prior to examination of the present Application, Applicants respectfully request that the above-identified application be amended as follows:

IN THE SPECIFICATION:

Page 1, line 5, after "starch" insert --or starch--.

IN THE CLAIMS:

Claim 3, line 1, delete "or 2".

Claim 4, lines 1 and 2, delete "one or more of claims 1 to 3" and insert --claim 1--.

Claim 5, lines 1 and 2, delete "one or more of claims 1 to 4" and insert --claim 1--.

Claim 6, lines 1 and 2, delete "one or more of claims 1 to 5" and insert --claim 1--.

Claim 7, lines 1 and 2, delete "one or more of claims 1 to 6" and insert --claim 1--.

Claim 8, lines 1 and 2, delete "one or more of claims 1 to 7" and insert --claim 1--.

Claim 9, lines 1 and 2, delete "one or more of claims 1 to 8" and insert --claim 1--.

Claim 10, lines 1 and 2, delete "one or more of claims 1 to 9" and insert --claim 1--.

Claim 11, line 2, delete "one or more of claims 1 to 9" and insert --claim 1--.

Claim 12, lines 1 and 2, delete "one or more of claims 1 to 10" and insert --claim 1--.

REMARKS


Applicants respectfully request that the foregoing amendments to Claims 3-12 be entered. These amendments are being made in order to avoid this application incurring a surcharge for the presence of one or more multiple dependent claims. No new matter has been added.

Respectfully submitted,

Date July 14, 2000

FOLEY & LARDNER
Washington Harbour
3000 K Street, N.W., Suite 500
Washington, D.C. 20007-5109
Telephone: (202) 672-5414
Facsimile: (202) 672-5399

By


for Richard L. Schwaab
Attorney for Applicant
Registration No. 25,479

**Sausage casing containing starch or starch derivatives and
production process**

5 The invention relates to sausage casings made from blends of
thermoplastic starch derivatives with biodegradable,
hydrophilic, suppleness-inducing polymers and suitable other
additives with or without crosslinkers.

10 Most sausage casings consist of natural skins, but also of
fiber-reinforced regenerated cellulose, collagen or synthetic
polymers. Although cellulose and collagen are of natural
origin, the sausage casings are produced in complex and
environmentally-polluting processes. Casings made of other
15 material, for example of protein- or acrylic-coated cloth, in
contrast, are of only minor importance.

20 Of the known casings, only those made of cellulose hydrate
cover the entire spectrum of applications. Collagen casings,
for some applications, have an excessive water-vapor or oxygen
permeability. The casings made of synthetic polymers are
unsuitable for producing long-keeping sausage. Although they
may be produced inexpensively and simply, for example by
extrusion, in contrast to the cellulose hydrate casings or
collagen casings, they are not biodegradable.

25 Although the sausage casing which is described in
EP-A 0 709 030, produced by extrusion of thermoplastic starch,
is biodegradable, it still has deficiencies. In particular it
is not sufficiently cooking-stable and has a tendency to
30 embrittle after water treatment or as a result of loss of
plasticizer.

35 Therefore there still remained the object of developing a food
casing which may be produced from natural, as far as possible
renewable, raw materials by simple and environmentally
acceptable processes, as far as possible by an extrusion
process, and at the same time is biodegradable or at least

compostible. The casing must be sufficiently permeable and usable for virtually all types of sausage, inter alia, therefore, for the production of cooked-meat sausages and scalded-emulsion sausages, and also of raw sausages.

5

The object is achieved by a blend of thermoplastic starch or a thermoplastic starch derivative and one or more synthetic polymers. The present application thus relates to a seamless tubular food casing which is blown in an area ratio of from 1:2 to 1:10, is produced from a thermoplastic mixture which comprises a) thermoplastic starch and/or a thermoplastic starch derivative and b) at least one other polymer obtainable by polycondensation or polyaddition, the weight ratio a):b) being in the range from 90:10 to 10:90.

10

15

The thermoplastic starch derivative is preferably a starch ester as described extensively in DE-A 195 15 477. The acid component in the ester is generally a (C₂-C₁₀) alkanolic acid which is preferably unbranched or branched only to a small extent. A particularly preferable and inexpensive starch alkanolate is starch acetate, in particular that having a degree of substitution less than 3, specifically from 1.5 to 2.4. Starch esters, such as starch acetate, which are different from starch itself, are already thermoplastic as such and do not need to be plasticized first. Starch esters having a relatively long alkyl chain, for example starch hexanoates, starch octanoates or starch decanoates, cause a change in the suppleness and toughness and also the permeation of the food casings. By combining different starch esters, casings having quite specific properties may be produced. Thermoplastic starch derivatives which have cationic quaternary side groups containing hydrophobic (C₂-C₁₈) alkyl groups, preferably (C₂-C₁₂) alkyl groups, are also suitable.

20

25

30

It has been found that food casings which consist only of thermoplastic starch and/or thermoplastic starch derivatives still do not have the desired level of extensibility,

35

strength, toughness, suppleness, but also primarily stability to hot or boiling water. The properties of the casing were not improved significantly even when other low-molecular-weight substances, such as lubricants, plasticizers and fillers, were added to the thermoplastic starch or the thermoplastic starch derivative. Surprisingly, it has been found that significant improvement does not occur until the thermoplastic starch or the starch derivative is blended with other polymers which are obtainable by polycondensation or polyaddition and are safe for food packaging.

The polymer obtainable by polycondensation is preferably a homopolymer or copolymer containing hydroxycarboxylic acid units. Particularly preferably it is a polylactide, poly(3-hydroxypropionic acid), poly(3-hydroxybutyric acid), poly(4-hydroxybutyric acid), polycaprolactone, polyesterurethanes, polyetherurethanes and polyesteretherurethanes. Polyalkylene carbonates of the formula $-[\text{CHR}^1-\text{CHR}^2-\text{O}-\text{CO}-\text{O}]_n$, where R^1 and R^2 independently of one another are a hydrogen atom or a (C_1-C_4) alkyl radical and n is an integer from 10 to 5000. Particularly suitable polyalkylene carbonates are polyethylene carbonate ($\text{R}^1=\text{R}^2=\text{H}$) and polypropylene carbonate and mixtures thereof. The polyalkylene carbonates are described, for example, in WO 96/35746. A preferred polymer which is obtainable by polyaddition is polyvinyl acetate. The polycondensation or polyaddition products may be prepared synthetically by known processes. They are usually not crosslinked or crosslinked only to a small extent. Their mean molecular weight M_w is generally from 20,000 to 2,000,000, preferably from 100,000 to 1,000,000. It is assumed that the polycondensates form a type of matrix in which the thermoplastic and thus non-structured starch or the starch derivative is uniformly distributed.

The weight ratio of the components a):b) is preferably from 20:80 to 80:20, particularly preferably from 40:60 to 60:40.

In addition to the components a) and b), the thermoplastic mixture can further comprise other low-molecular-weight or high-molecular-weight constituents which act in particular as plasticizers or lubricants or improve the compatibility of the components with one another. As a result of the further constituents the homogeneity or flowability of the extrudable thermoplastic mixture can if appropriate be further improved. Suitable plasticizers are particularly glycerol, diglycerol, sorbitol, polyethylene glycol (PEG), citric acid triethyl ester, acetylcitric acid triethyl ester, glycerol triacetate, phthalic esters (especially dimethyl phthalate, diethyl phthalate and dibutyl phthalate) and sorbitol monoesters and diesters. The proportion of plasticizer(s) is up to 30% by weight, preferably up to 15% by weight, in each case based on the total weight of the thermoplastic mixture. Lubricants which improve the homogeneity of the thermoplastic mixture are, in particular, vegetable fats or oils, synthetic triglycerides, lecithins, ethoxylated fatty alcohols or waxes. The proportion of lubricants is up to 12% by weight, preferably from 2 to 6% by weight, particularly preferably from 3 to 6% by weight, in each case based on the total weight of the mixture.

The casing of the invention can finally further be reinforced with fibers. Generally, the fibers are relatively short (on average about 0.1 to 3 mm, preferably from 0.2 to 1.5 mm). In order that the casing remains biodegradable and thus compostible, fibers of cotton linters, wood pulp, regenerated cellulose ("regenerated fibers"), of hemp, flax, sisal or jute are particularly suitable. The proportion of fibers can be up to 25% by weight.

Preferably, the fiber content is from 2 to 15, in particular from 5 to 15, % by weight, in each case based on the total weight of the mixture. The fibers are uniformly distributed in the thermoplastic mixture or the extrudable melt produced therefrom.

The casing can further contain fillers, either instead of the fibers or additionally. Suitable fillers are, for example, calcium carbonate, talc, kaolin or anhydride (= calcium sulfate). The proportion of fillers can be up to 12% by weight, but preferably it is from 2 to 8% by weight, particularly preferably from 4 to 8% by weight, in each case based on the total weight of the thermoplastic mixture.

For casings having a particularly high stability to hot or boiling water it has proved to be expedient also to add crosslinkers to the thermoplastic mixture. Suitable crosslinkers are, for example, dicarboxylic acids, diisocyanates or triisocyanates (particularly hexamethylene diisocyanate), dialdehydes (particularly glyoxal), diepoxides, diimines or silanes or siloxanes containing vinyl group(s), for example vinyltrimethylsilane. The crosslinker is preferably not added until the remaining components of the mixture are already molten. The proportion of crosslinker(s) is up to 20% by weight, preferably from 0.5 to 10% by weight, particularly preferably from 1 to 5% by weight, in each case based on the total weight of thermoplastic mixture.

The production of thermoplastic starch is known and described in WO 90/05161 and 90/10019. During the plasticization, the helix structure of the native starch is destroyed. The starch is thereafter in an amorphous state. The plasticization is generally performed by heating and supplying mechanical energy, for example by relatively long thermal treatment in a kneader or in a single- or double-screw extruder. In order that the starch melts below its decomposition temperature, additives are necessary, such as water, 1,3-butanediol, glycerol, diglycerol, N,N-dimethylurea, sorbitol or citrate. In the case of plasticization using water, from about 20 to 25% by weight of water, preferably about 17% by weight of water, are added, in each case based on the weight of the native starch. A temperature of from about 100 to 130°C is maintained in the course of this. In the case of plasticiz-

ation using glycerol, a proportion of from 0.5 to 20% by weight, preferably from 8 to 16% by weight, again in each case based on the weight of the native starch, and a temperature of from 150 to 170°C have proved expedient. Owing to this treatment, the proportion of crystalline starch is decreased to 5% by weight or even less.

The thermoplastic mixture may be prepared from said components in conventional apparatuses, for example in a double-screw kneader. To form a homogeneous, thermoplastic melt from the mixture, a temperature of from 90 to 200°C, preferably from 120 to 180°C, has proved to be expedient. The melt can be extruded, comminuted after cooling and stored temporarily as granules or in similar form or equally well be processed directly to a food casing. The tube produced from the described melt is then expanded with air in the blown film extrusion process and stretched longitudinally and transversely in an area ratio of from 1:2 to 1:10, preferably from 1:3 to 1:5. Not until the stretching do the tubes achieve the optimum strength, elongation, caliber constancy and shrinkage. The extent to which each of these properties is expressed primarily depends on the composition of the thermoplastic mixture. Thus the food casings, by a targeted selection of the components of the thermoplastic mixture, the stretching conditions and the type of post-treatment, can be adapted to the most varied requirements. If appropriate, the blown casings can also in some cases be thermoset.

In a further process step, preparations can be applied to the tubular casings internally and/or externally in order to make them still more suitable for the various applications as sausage casing. For this there may be used most liquid preparations which are also customary for the surface finishing of cellulose hydrate casings, in a concentration adapted accordingly. Thus, it is particularly expedient to coat with protein (preferably casein, gelatin, soy protein or wheat protein) the inner surface of a casing intended for

5 long-keeping sausage. The protein is customarily in this case bound to the casing surface using an aldehyde. By using resins or by adding release agents to the protein/aldehyde, the peelability of the sausage casing can be set. The adhesion of the casing to the sausagemeat emulsion may be reduced to a strong release action using known formulations (this is required, for example, in the case of Thüringer Blutwurst).

10 Suitable external preparations are also already known from cellulose casings. By treating the outer surface of the casing with such a preparation, in particular, mold resistance, surface roughness and printability may be set.

15 The food casing of the invention can have its properties varied to the extent that it corresponds to a cellulose casing or a plastic casing. It may be produced by simple and environmentally compatible processes. Its good swelling and shrinkage properties means that it always lies tightly against the sausagemeat emulsion and that no creases form even during
20 slow drying. By a selection of the components, the permeability of the casing for water, water vapor and oxygen can be set exactly. Surprisingly, the casing is even permeable for smoke, so that it is also readily suitable for smoked sausage types (for example salami). The starch used for producing the
25 casing furthermore is a particularly expedient renewable raw material.

30 The casing of the invention can finally also be enclosed by a, preferably broad-mesh net, which imparts a particularly attractive appearance to the finished product. It consists of a tubular net which is known for wrapping sausages and is adapted to the periphery of the carrier tube. The thickness shall be at least ... mm, so that the net stands out clearly. Very different mesh shapes are used: triangular, hexagonal,
35 square, diamond-shaped, round or oval. The meshes themselves are formed from individual filaments or filaments entwined together and usually consist of textile filaments, preferably

of a material which resembles the carrier tube. In contrast to the net disclosed by DE-A 39 07 951, adhesive is no longer required, since the casing of the invention adapts to the net structure and thus ensures the desired adhesion.

5

In the examples hereinafter, percentages are percentages by weight, unless stated otherwise.

Example 1:

10

a) Production of thermoplastic starch

15

100 kg of potato starch were dried under reduced pressure to a water content less than 0.3% and melted together with 50 kg of glycerol (99% pure) in a kneader at from 160 to 190°C and mixed well. To destroy the helix structure of the starch, the melt was kept at 170°C for about 2 h. It was then extruded and granulated. During subsequent storage of the granules, the starch remained in the amorphous and thus thermoplastic stage.

20

b) Production of an unreinforced seamless food casing:

25

75 kg of the granules described under a) (50 kg of starch + 25 kg of glycerol) were mixed with 50 kg of polycaprolactone, 3 kg of sunflower seed oil and 3 kg of hexamethylene diisocyanate. The components which were evenly mixed with one another were melted in an extruder at 150°C. The melt was then extruded through an annular die. The diameter of the annular die was chosen so that after the film blowing in an area ratio 1:10 a tube having a diameter of 60 mm (= caliber 60) and a wall thickness of 80 µm was obtained.

30

The tubes are stable in water, but swell therein and shrink again on drying. They can be placed on the stuffing apparatus in the form of sections tied-off at one end or in a consolidated form as what are termed "shirred sticks". They are suitable in particular as casings for long-keeping sausage (that is for a raw sausage having a particularly high degree of maturation).

35

In the water-impregnated state, a bursting pressure of from 25 to 35 kilopascals (kPa) was achieved. The static elongation at 15 kPa internal pressure was from 68 to 76 mm. The casings were stuffed with salami emulsion. The adhesion to the emulsion was low (peelability after 2 weeks: "1" on a scoring scale from 1 to 6, where "1" is very easily peelable" and "6" is "excessively strong adhesion, casing cannot be removed without damage").

To increase the emulsion adhesion, therefore, a protein (casein)/glyoxal internal preparation was applied, as is customary with cellulose hydrate tubes.

Example 2:

A blend was produced from 50 kg of starch acetate having a degree of substitution of 2.2 and a molar mass of 580 g/mol which was mixed with 50 kg of polyethylene carbonate having a molecular weight M_w of 500,000 and 15 kg of citric acid triethyl ester were added. To this mixture was added 8 kg of thermoplastic starch, 5 kg of 1,2:5,6-diepoxyhexane (hexamethylene diepoxide) and 5 kg of ethoxylated octadecanol (stearyl alcohol), on average 12 ethylene oxide units.

This mixture was melted at from 150 to 170°C in a double-screw extruder, mixed well and then extruded through an annular die whose dimensions were selected such that after blown film extrusion in an area ratio of 1:8 a tube of caliber 70 having a wall thickness of 90 μ m was obtained.

The tube thus produced was resistant to simmering; it swelled in water and shrank again on drying.

In the water-impregnated state, a bursting pressure of from 38 to 42 kPa was achieved. The static elongation at 15 kPa internal pressure was from 76 to 80 mm.

Sections tied off at one end or shirred were suitable for producing long-keeping sausage and scalded-emulsion sausage. The peelability was good with both types of sausage (score: 2).

5
Example 3 (Production of a fiber-reinforced casing):

A blend of 50 kg of starch acetate, 15 kg of citric acid triethyl ester and 50 kg of polyethylene carbonate was mixed uniformly in the melt with 10 kg of flax fibers of length from 10 0.2 to 1.5 mm. The melt was extruded through an annular die at from 160 to 180°C and blown (area stretching ratio 1:6), so that a tube of caliber 60 was obtained. The water-impregnated tubes achieved a bursting pressure of from 60 to 65 kPa and a static elongation of from 65 to 70 mm at 21 kPa internal 15 pressure.

The casings could be used for scalded-emulsion sausage and long-keeping sausage. They achieved a stuffing caliber of from 16 66 to 68 mm and could be peeled easily.

20
Example 4:

A polymer blend as described in Example 1 was evenly mixed in the melt with 12% cotton linters, extruded and blown via an annular die, so that at a longitudinal and transverse 25 stretching in an area ratio of 1:10 a tube of caliber 50 was obtained.

In the water-impregnated state, a bursting pressure of from 30 60 to 68 kPa was measured and a static elongation of from 56 to 62 mm at 21 kPa internal pressure was measured.

The stuffing caliber for scalded-emulsion sausage and long-keeping sausage was from 57 to 62 mm. The peelability was 35 good.

1. A seamless, tubular food casing which is blown in an area ratio of from 1:2 to 1:10, produced from a thermoplastic mixture which comprises a) thermoplastic starch and/or a thermoplastic starch derivative and b) at least one other polymer obtainable by polycondensation or polyaddition, the weight ratio of a):b) being in the range from 90:10 to 10:90.
2. The food casing as claimed in claim 1, wherein the thermoplastic starch derivative is a starch ester, preferably a starch alkanoate, particularly preferably starch acetate.
3. The food casing as claimed in claim 1 or 2, wherein the polymer obtainable by polycondensation is a homopolymer or copolymer containing hydroxycarboxylic acid units, preferably a polylactide, a poly(3-hydroxypropionic acid), a poly(3-hydroxybutyric acid), a poly(4-hydroxybutyric acid), polycaprolactone, a polyesterurethane, polyetherurethane, a polyesteretherurethane or a polyalkylene carbonate of the formula $-[\text{CHR}^1-\text{CHR}^2-\text{O}-\text{CO}-\text{O}]_n$, where R^1 and R^2 independently of one another are a hydrogen atom or a (C_1-C_4) alkyl radical and n is an integer from 10 to 5000.
4. The food casing as claimed in one or more of claims 1 to 3, wherein the weight ratio a):b) is in the range from 20:80 to 80:20, preferably in the range from 40:60 to 60:40.
5. The food casing as claimed in one or more of claims 1 to 4, wherein the thermoplastic mixture comprises at least one plasticizer, preferably glycerol, diglycerol, sorbitol, polyethylene glycol, citric acid triethyl ester, acetylcitric acid triethyl ester, glycerol

triacetate, a phthalic ester or sorbitol monoester or sorbitol diester, the proportion of plasticizer(s) being up to 30% by weight, preferably up to 15% by weight, in each case based on the total weight of the thermoplastic mixture.

6. The food casing as claimed in one or more of claims 1 to 5, wherein the thermoplastic mixture comprises at least one lubricant, preferably a vegetable fat or a vegetable oil, a synthetic triglyceride, lecithin, an ethoxylated fatty alcohol or a wax, the proportion of lubricant(s) being up to 12% by weight, preferably from 2 to 6% by weight, particularly preferably from 3 to 6% by weight, in each case based on the total weight of the thermoplastic mixture.
7. The food casing as claimed in one or more of claims 1 to 6, wherein the thermoplastic mixture is mixed with fibers, preferably fibers from cotton linters, wood pulp, from regenerated cellulose, from hemp, flax, sisal or jute, the proportion of fibers being up to 25% by weight, preferably from 2 to 15, particularly preferably from 5 to 15, % by weight, in each case based on the total weight of the mixture.
8. The food casing as claimed in one or more of claims 1 to 7, wherein the thermoplastic mixture comprises fillers, preferably calcium carbonate, talc, kaolin or anhydrite, the proportion of fillers being up to 12% by weight, preferably from 2 to 8% by weight, particularly preferably from 4 to 8% by weight, in each case based on the total weight of the mixture.
9. The food casing as claimed in one or more of claims 1 to 8, wherein the thermoplastic mixture comprises at least one crosslinker, preferably a dicarboxylic acid, a diisocyanate or triisocyanate, a dialdehyde, a di-

epoxide, a diimine or a silane or siloxane containing vinyl group(s), the proportion of crosslinker(s) being up to 20% by weight, preferably from 0.5 to 10% by weight, particularly preferably from 1 to 5% by weight, in each case based on the total weight of the mixture.

10. The food casing as claimed in one or more of claims 1 to 9, wherein it is provided with an internal preparation and/or external preparation.

11. A process for producing the food casing as claimed in one or more of claims 1 to 9, which comprises extruding the thermoplastic mixture through an annular die and blowing it in an area ratio of from 1.2 to 1:10.

12. The use of the food casing as claimed in one or more of claims 1 to 10 as synthetic sausage casing.

ABSTRACT

The invention relates to a seamless tubular food casing. Said casing is shaped by blowing with a surface area ratio of 1:2 to 1:10 and is produced from a thermoplastic mixture comprising a) thermoplastic starch and/or thermoplastic starch derivative and b) at least one other polymer obtained by polycondensation or polyaddition, the weight ratio a):b) being 90:10 to 10:90. The thermoplastic mixture may also contain plasticiser, lubricants, fibres, fillers and/or crosslinking agents. The inventive casing is especially suitable for use as a plastic sausage casing.

DECLARATION AND POWER OF ATTORNEY

As a below-named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

SAUSAGE CASING WITH STARCH OR STARCH DERIVATIVES AND METHOD FOR PRODUCTION THE SAME

the specification of which is attached hereto unless the following box is checked:

☒ was filed on **February 6, 1999** as United States Application Number or PCT International Application Number **PCT/EP99/00801** and was amended on _____ (if applicable).

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is known by me to be material to patentability as defined in Title 37, Code of Federal Regulations § 1.56.

I hereby claim foreign priority benefits under Title 35, United States Code, § 119 (a)-(d) or § 365 (b) of any foreign application(s) for patent or inventor's certificate, or § 365 (a) of any PCT International Application which designated at least one country other than the United States, listed below and have also identified below any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application on which priority is claimed:

PRIOR FOREIGN APPLICATION(S)

NUMBER	COUNTRY	DAY/MONTH/YEAR FILED	PRIORITY CLAIMED
198 05 925.6	Federal Republic of Germany	13 February 1998	YES

I hereby claim the benefit under Title 35, United States Code §119 (e) of any United States provisional application(s) listed below:

APPLICATION NUMBER	FILING DATE

I hereby claim the benefit under Title 35, United States Code, § 120 of any United States application(s), or § 365 (c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of Title 35, United States Code, § 112, I acknowledge the duty to disclose information which is known by me to be material to patentability as defined in Title 37, Code of Federal Regulations § 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of this application:

APPLICATION SERIAL NO.	FILING DATE	STATUS: PATENTED, PENDING, ABANDONED

I hereby appoint as my attorneys, with full powers of substitution and revocation, to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith: Stephen A. Bent, Reg. No. 29,768; David A. Blumenthal, Reg. No. 26,257; William T. Ellis, Reg. No. 26,874; John J. Feldhaus, Reg. No. 28,822; Patricia D. Granados, Reg. No. 25,735; John P. Isacson, Reg. No. 33,715; Michael D. Kaminski, Reg. No. 32,904; Kenneth E. Krosin, Reg. No. 25,735; Eugene M. Lee, Reg. No. 32,039; Richard Linn, Reg. No. 25,144; Peter G. Mack, Reg. No. 26,001; Brian J. McNamara, Reg. No. 32,789; Sybil Meloy, Reg. No. 22,749; George E. Quillin, Reg. No. 32,792; Colin G. Sandercock, Reg. No. 31,298; Bernhard D. Saxe, Reg. No. 28,665; Charles F. Schill, Reg. No. 27,590; Richard L. Schwaab, Reg. No. 25,479; Arthur Schwartz, Reg. No. 22,115; Harold C. Wegner, Reg. No. 25,258.

Address all correspondence to **Foley & Lardner**, 3000 K Street, N.W., Suite 500, P. O. Box 25696, Washington, D.C. 20007-8696.
Address telephone communications to **Richard L. Schwaab** at (202)672-5300.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of this application or any patent issued thereon.

Full name of First or Sole Inventor <i>Klaus-Dieter HAMMER</i>	Signature of First or Sole Inventor <i>Klaus-Dieter Hammer</i>	Date June 23, 2000
Residence Address <i>Mainz, Federal Republic of Germany</i>	Country of Citizenship <i>Federal Republic of Germany</i>	
Post Office Address <i>An der Hasenquelle 25, D-55120 Mainz, Federal Republic of Germany</i>		

Full name of Second Inventor <i>Gerhard GROLIG</i>	Signature of Second Inventor <i>Gerhard Grolig</i>	Date June 23, 2000
Residence Address <i>Moerfelden-Walldorf, Federal Republic of Germany</i>	Country of Citizenship <i>Federal Republic of Germany</i>	
Post Office Address <i>Gartenstrasse 3, D-64546 Moerfelden-Walldorf, Federal Republic of Germany</i>		

Full name of Third Inventor <i>Michael AHLERS</i>	Signature of Third Inventor <i>Michael Ahlers</i>	Date June 23, 2000
Residence Address <i>Mainz, Federal Republic of Germany</i>	Country of Citizenship <i>Federal Republic of Germany</i>	
Post Office Address <i>Im Muenchfeld 13, D-55122 Mainz, Federal Republic of Germany</i>		

Full name of Fourth Inventor	Signature of Fourth Inventor	Date
Residence Address	Country of Citizenship	
Post Office Address		

Office Address of all Inventors:

Kalle Nalo GmbH & Co. KG
Rheingastrasse 190-196, Industriepark Kalle-Albert
D-65203 Wiesbaden, Federal Republic of Germany